

REPORT TO: Sealmark Corporation  
P.O. Box 206C Locust Road  
Coal Center, PA 15423

Project No. 823-66078  
Laboratory No. SPT-60104  
Report Date: October 4, 1996

REPORT OF: Falling Sand Abrasion of Sealmark Coating

---

GENERAL

The sample identified above was tested for its abrasion resistance per ASTM D968-93, "Standard Test Methods for Abrasion Resistance of Organic Coatings by Falling Abrasive," Method A, "Falling Sand Abrasion Test". The following results were obtained.


TEST RESULTS

Coating Thickness: 8.5 mils

No wear through to the substrate was obtained after 1060 liters impinged on the surface.

Prepared by:

Reviewed and Approved by:



Mike Bracken  
Senior Lab Technician



Tim Barefoot, Manager  
Special Test Department