



KTA-TATOR, INC.
115 Technology Drive, Pittsburgh, PA 15275

(412) 788-1300
FAX (412) 788-1306
<http://www.kta.com>
e-mail: info@kta.com

PROTECTIVE COATINGS (PAINT) CONSULTANTS: Testing • Instruments • Inspection • Analytical Laboratory
September 18, 1997

Mr. Joseph Burke
Sealmark Corporation
207 Marine Street
Belle Vernon, PA 15012

SUBJECT: Testing of Coating Sample for Volatile Organic Content (VOC)

Dear Mr. Burke:

In accordance with your letter of September 15, 1997, KTA-Tator, Inc. has tested a sample of latex coating to determine its VOC.

The sample, labeled "Sealmark Corporation, Sealmark Coating, 9-15-97" was received from Sealmark on September 16, 1997. It was tested for VOC in accordance with ASTM D-3960, which involves determining the percent water in accordance with ASTM D-3792, the weight solids in accordance with ASTM D-2369, and the weight per gallon in accordance with ASTM D-1475.

When tested according to the above methods, the coating was found to contain 0 VOC.

Should you have any further questions or comments, please do not hesitate to contact this office.

Very truly yours,

KTA-TATOR, INC.

Dwight G. Weldon

DGW/RNR:rk

JN 970712

NOTICE: This report represents the opinion of KTA-Tator, Inc. This report is issued in conformance with generally acceptable industry practices. While every precaution was taken to insure that all information gathered and presented is accurate, complete and technically correct, it is based on the information, data, time, materials, and/or samples afforded.